

**Description:**

Stranco S-454 is a flame retardant 1 mil (25 $\mu$ ) polyimide film with a high-temperature permanent pressure sensitive acrylic adhesive and a high opacity, gloss white topcoat specifically designed for thermal transfer printing. Using a 1 mil vs. a 2 mil polyimide film base offers polyimide thermal performance at less cost.

**Properties:**

The S-454 topcoat, in combination with the appropriate thermal transfer ribbon, passes the requirements of **MIL-STD-202G, Notice 12, Method 215K** and **MIL-STD-883E, Notice 4, Method 2015.13**. The print resists smearing, even when the board and label are directly removed from a reflow or wave solder environment. S-454 also meets UL510 OANZ2 Flammability rating see UL file no. E323067

**Applications:**

- PCB identification
- Electronic components
- Hand held devices
- Harsh chemical requirements
- IC labeling for work in process, permanent ID & warranty labeling
- Product ID, asset tracking
- Anywhere a label will be exposed to extreme temperatures

**Special Considerations:**

- The surface that you want to label should be clean, dry and free of any surface contamination, such as dust, oil or rust. Isopropyl alcohol would be a recommend solvent to clean the surface.
- When you apply the label, you must use firm pressure to increase the physical contact of the adhesive with the surface of the product.
- Pressure sensitive adhesives will provide stronger bonds to a warm surface, as compared to a colder one. The adhesive will 'flow' more readily, increasing the surface area and increasing the adhesion peel strength.
- Preheating the labeled product can further enhance print permanence in the case of extreme solvent and/or abrasion exposure, although this is not typically required for board processing applications.
- The S-454 top coat & print should not be contacted while exposed to elevated temperature.
- All values shown are averages and should not be used for specification purposes. Adhesion and tack values have a 15% tolerance allotted to the above values stated.
- Test data and test results contained in this document are for general information only and shall not be relied upon by Stranco customers for designs and specifications, or be relied on as meeting specified performance criteria.



# S-454

## Thermal Transfer Printable Polyimide

### 1 mil GLOSS WHITE

#### Technical Data

PROPERTIES	TEST METHODS	AVERAGE RESULTS	
		USA Units	SI Units
<b>Thickness</b>	<b>ASTM D1000</b>		
-Face sheet		0.0015 inch	0.038 mm
-Adhesive		0.0010 inch	0.025 mm
-Total		0.0025 inch	0.063 mm
<b>Adhesion</b>	<b>80313</b>		
-Stainless Steel	<b>20 minute dwell</b>	≥ 25 oz/in	27N/100 mm
	<b>24 hour dwell</b>	≥ 28 oz/in	31N/100 mm
<b>Tack</b>	<b>80155</b>	≥ 1000 g/in	
<b>Weatherometer Testing</b>	<b>ASTM G154</b>	No Visible Effect	
<b>Temperature Rating:</b>	<b>Long term</b>	100 hours at 302°F (150°C)	
	<b>Operating</b>	5 minutes at 500°F (260°C)	
	<b>Short term</b>	90 seconds at 572°F (300°C)	
<b>Outgas Testing</b>	<b>ASTM E595</b>	TML 0.62%, CVCM <0.01%, WVR 0.57%	
<b>Shelf Life</b>	<b>1 year below 80°F (27°C) and 60% R.H.</b>		
<b>UL File #</b>	PGJI2.MH19503		
<b>CUL File #</b>	PGJI8.MH19503		
<b>UL approved ribbons</b>	Ricoh B110CR, C, Armor AXR 7+, 8, DNP R510		
<b>CUL approved ribbons</b>	Ricoh B110CR, C, DNP R510, JPP1, Armor AXR7+, 8		

#### Durability Testing

Properties	Test Methods	Test Environment	PCS <sup>1</sup>	Read Rate <sup>2</sup>
<b>Heat / Chemical</b>	<b>80386</b>	Control 70°C	99%	100%
		Alpha Metals Inc. 2110 Saponifier 10% aqueous, 70°C, 5 min.	97%	100%
		Isopropanol 99%, 70°C, 5 min.	99%	100%
		Kyzen XJN 30%, 70°C, 5 min.	99%	100%

#### Chemical Testing

Properties	Test Method	Test Fluid	Results
<b>Chemical Resistance</b>	<b>MIL-STD-202G, Notice 12, Method 215K MIL-STD-883E, Notice 4, Method 2015.13</b>		
		Solvent A-1part IPA, 3 parts Mineral Spirits	No visible effect
		Solvent B- 1,1,1 Trichloroethane	Solvent deleted per notice 12
		Solvent C- Terpene Defluxer	No visible effect
		Solvent D- Saponifier	No visible effect

#### Material Compliance

<b>RoHS- Restriction of Hazardous Substances (EU Directive 2002/95/EC)</b>	Limits set forth in Directive 2005/618/EC amending Directive 2002/95/EC
<b>REACH- Registration Evaluation and Authorization of Chemicals (EU Directive 1907/2006/EC)</b>	Limits set forth in Directive 1907/2006/EC Article 7 (2)
<b>Halogens- Restriction use of Halogen (IEC 61249-2-21)</b>	Limits set in International Electrochemical Commission

**5/20/2015**

**Key for the Tables on page 2**

- All SI units are mathematically derived from U.S. conventional units.
- Labels printed with recommended thermal transfer ribbon. Labels printed with 6.7 mil X dimension bars at 2:5 ratio. Labels exposed to indicated environments.
- PCS<sup>1</sup>- Print Contrast Signal. PCS determined with Quick Check 650, 0.0005" aperture, 660 nm wavelength
- Quick check 650 manufactured by: Photographic Sciences Corp.
- <sup>2</sup> Read rate determined using a PSC Quick Check 850 laser scanner

**Trademarks:**

XJN & Aquanox™ is a trademark of Kyzen Corporation.

**References:**

ASTM: American Society for Testing and Materials (U.S.A.)  
 SI: International Systems of Units.



**WARRANTY-LIMITATION**

Stranco's products are sold with the understanding that the buyer will test them in actual use and determine for him/herself their adaptability to his/her intended uses. Stranco warrants to the buyer that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the products shown to Stranco's satisfaction to have been defective, provided that the Buyer has complied with the handling, storage and shelf life requirements as specified by Stranco in applicable materials specifications.

The above warranties extend solely to Buyer and all warranty claims must be made by Buyer. Rework or Replacement shall neither extend nor decrease the original warranty period. The term of all warranty periods shall not exceed thirty (30) days from the date of the original shipment.

**THE ABOVE WARRANTIES ARE EXCLUSIVE OF AND IN LIEU OF ALL OTHER WARRANTIES, WRITTEN OR ORAL, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE. NO IMPLIED STATUTORY WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. STRANCO SHALL NOT BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OR INABILITY TO USE THE PRODUCT, OR FROM DELAY IN THE REPLACEMENT OR REPAIR OF PRODUCTS UNDER THE ABOVE WARRANTY.**